

— CELEBRATING —
★
28th
YEARS
— ANNIVERSARY —
★


VASANI
POLYMERS PVT. LTD.

Delivering Pipes,
Building Trust

CPVC Plumbing Pipes & Fittings



Vasani Polymers Pvt. Ltd.

Manufacturing Unit

Survey No 488/p & 519/p GIDC Talod - 383215,
Dist: Sabarkantha, Gujarat, India.

Corporate Office

D/604, Ganesh Meridian, Opp. Gujarat High Court,
S.G. Highway, Sola, Ahmedabad, Gujarat, India - 380060

info@vasanipolymers.com | sales@vasanipolymers.com

Customer Care : +91-9409309800

www.vasanipolymers.com



CPVC Plumbing Pipes & Fittings



PRODUCT BRIEF :

- Material: Chlorinated Polyvinyl Chloride (CPVC)
- Pressure Rating : SDR 11 & 13.5
- Size: ½" - 2"
- Standard : IS 15778
- Colour: Ivory
- Form Supplied : CPVC Plumbing pipe with 3m

ADVANTAGE :

- Highly durable
- Corrosion resistance
- Ultra Violet Stabilized
- Lead free Non-toxic
- Low Thermal Expansion
- Earthquake resistant
- Eco friendly
- Easy Instalation

APPLICATION :

- Ideal for Hot & Cold Water Application
- Residential Purposes
- Chemical Fluid
- Industrial Use
- Corrosive Fluid Transportation
- Can be used with solar water heater

CPVC Pipe SDR 11									
Nominal Bore		Mean Outside Diameter (mm)		Wall Thickness		Working Pressure at 27°C		Working Pressure at 82°C	
(Inch)	(mm)	Average	Tolerance	(mm)	Tolerance	Kg/Cm ²	(MPA)	Kg/Cm ²	(MPA)
½"	15	15.9	±0.1	1.95	±0.25	28.14	2.76	6.93	0.68
¾"	20	22.2	±0.1	2.25	±0.25	28.14	2.76	6.93	0.68
1"	25	28.6	±0.1	2.85	±0.25	28.14	2.76	6.93	0.68
1¼"	32	34.9	±0.1	3.45	±0.25	28.14	2.76	6.93	0.68
1½"	40	41.3	±0.1	4.05	±0.25	28.14	2.76	6.93	0.68
2"	50	54.0	±0.1	5.20	±0.25	28.14	2.76	6.93	0.68

CPVC Pipe SDR 13.5									
Nominal Bore		Mean Outside Diameter (mm)		Wall Thickness		Working Pressure at 27°C		Working Pressure at 82°C	
(Inch)	(mm)	Average	Tolerance	(mm)	Tolerance	Kg/Cm ²	(MPA)	Kg/Cm ²	(MPA)
½"	15	15.9	±0.1	1.65	±0.25	22.23	2.18	5.61	0.55
¾"	20	22.2	±0.1	1.95	±0.25	22.23	2.18	5.61	0.55
1"	25	28.6	±0.1	2.35	±0.25	22.23	2.18	5.61	0.55
1¼"	32	34.9	±0.1	2.85	±0.25	22.23	2.18	5.61	0.55
1½"	40	41.3	±0.1	3.35	±0.25	22.23	2.18	5.61	0.55
2"	50	54.0	±0.1	4.30	±0.25	22.23	2.18	5.61	0.55